Typical Product Specifications & Properties

DERCOLYTE A 10

CAS Number::

Specifications	Limits
Description	DERCOLYTE A 10 is produced from the polymerisation of alpha pinene. It is a resin with a low soften
Solubility	Soluble in aromatic, aliphatic and chlorinated solvents. Insoluble in alcohol and ketones.
Stability	About 6 months storage conditions and inventory control must be observed.
Gardner Color	5 max (50 resin / 50 toluene)
Acid Value, mg KOH/g	1 max