



www.parchem.com



GIVE US A CALL  
800-282-3982  
914-654-6800

GET A QUICK QUOTE

## Typical Product Specifications & Properties

# Dimethylaminoethyl Methacrylate

CAS Number: : 2867-47-2

| Specifications              | Limits                |
|-----------------------------|-----------------------|
| Density                     | 0.933 (25 c)          |
| Color (APHA)                | 20 max                |
| Specific Gravity (20°C/4°C) | 0.930~0.936           |
| Purity                      | 98.5% min             |
| Water when shipped          | 0.2% max              |
| Inhibitor (MEHQ)            | 2000ppm               |
| Refractive Index, nD20      | 1.4414                |
| Viscosity at 20°C           | 1.34                  |
| Specific Heat               | 1.84                  |
| Flash Point                 | 65 C                  |
| Molecular weight            | 157.21                |
| Solubility                  | water and org. solvs. |



GET A QUICK QUOTE

415 Huguenot Street, New Rochelle, New York 10801

Disclaimer: this is a web generated product specification and property document. All information on this document is subject to reconfirmation at time of quote and order.




www.parchem.com



GIVE US A CALL  
800-282-3982  
914-654-6800

GET A QUICK QUOTE

| Specifications     | Limits                                                                                                                      |
|--------------------|-----------------------------------------------------------------------------------------------------------------------------|
| Boiling Point      | 182-190 c                                                                                                                   |
| Chemical Structure | <br>parchem<br>fine & specialty chemicals |



GET A QUICK QUOTE

415 Huguenot Street, New Rochelle, New York 10801

Disclaimer: this is a web generated product specification and property document. All information on this document is subject to reconfirmation at time of quote and order.