



www.parchem.com



GIVE US A CALL
800-282-3982
914-654-6800

GET A QUICK QUOTE

Typical Product Specifications & Properties

Lithium Tetraborate

CAS Number: : 12007-60-2

Specifications	Limits
Max of endothermic fusion	890C
Assay	typical 99.3%
MgO	typical 0.017%
CaO	typical 0.014%
Fe2O3	typical 0.013%
Molecular weight	169.12
Grain size	< 250 um
Bulk Density	about 0.3 g/ccm
Appearance	white powder
Melting Point	760-910C
Specific gravity	2.4 g/ccm
Na2O	typical 0.027%



GET A QUICK QUOTE

415 Huguenot Street, New Rochelle, New York 10801

Disclaimer: this is a web generated product specification and property document. All information on this document is subject to reconfirmation at time of quote and order.



www.parchem.com



GIVE US A CALL
800-282-3982
914-654-6800

GET A QUICK QUOTE

Specifications	Limits
Al ₂ O ₃	typical 0.02%
SiO ₂	typical 0.05%
Chemical Structure	



GET A QUICK QUOTE

415 Huguenot Street, New Rochelle, New York 10801

Disclaimer: this is a web generated product specification and property document. All information on this document is subject to reconfirmation at time of quote and order.