



www.parchem.com



GIVE US A CALL
800-282-3982
914-654-6800

GET A QUICK QUOTE

Typical Product Specifications & Properties

Magnesium Oxide-Technical Grade KP

CAS Number: : 1309-48-4

Specifications	Limits
Density	3.65-3.75
Melting Point	2800 c
Loss on ignition (900 C)	2.0% max
Bulk Density, tapped	0.45 - 0.75 gr/cc
Magnesium Oxide as MgO (by difference)	97.0% min
Calcium as CaO	1.00% max
Iron as Fe ₂ O ₃	0.05% max
Very Soluble	in water
Silicon as SiO ₂	0.10% max
Chloride as Cl	0.70% max
Sulphate as SO ₄	1.00% max
Residue on 100 mesh	10.0% max



GET A QUICK QUOTE

415 Huguenot Street, New Rochelle, New York 10801

Disclaimer: this is a web generated product specification and property document. All information on this document is subject to reconfirmation at time of quote and order.



www.parchem.com



GIVE US A CALL
800-282-3982
914-654-6800

GET A QUICK QUOTE

Specifications	Limits
Residue on 325 mesh	35.0% max
Insolubility	in alcohol
Odor	wh. powd. or cryst., odorless
Solubility	dil. acids, ammonium salt solns.
Molecular weight	40.31
Boiling Point	3600 c



GET A QUICK QUOTE

415 Huguenot Street, New Rochelle, New York 10801

Disclaimer: this is a web generated product specification and property document. All information on this document is subject to reconfirmation at time of quote and order.